



CLAIMS:

1. A release agent for use in silicone base rubber molding molds, comprising as essential components,
5 an organosilazane polymer comprising units represented by the general unit formula (1):



10 wherein R^1 is independently a perfluoroalkyl ether group, R^2 and R^3 are each independently hydrogen or a substituted or unsubstituted monovalent hydrocarbon group, Q is independently a divalent organic group, "a" is an integer of 1 to 3, "b" is an integer of 0 to 2, and the sum of a+b is an
15 integer of 1 to 3, and
an organic solvent capable of dissolving the polymer.

2. A release agent for use in silicone base rubber molding molds, comprising as essential components,
20 an organosilazane copolymer comprising units represented by the general unit formula (2):



25 wherein R^4 is independently a perfluoroalkyl or perfluoroalkyl ether group, R^2 and R^3 are each independently hydrogen or a substituted or unsubstituted monovalent hydrocarbon group, Q is independently a divalent organic group, "a" is an integer of 1 to 3, "b" is an integer of 0 to
30 2, and the sum of a+b is an integer of 1 to 3, and units represented by the general unit formula (3):



35 wherein R^2 and R^3 are as defined above, and "c" is an integer of 1 to 3, in a molar ratio of units (2)/units (3) between 95/5 and 50/50, and
an organic solvent capable of dissolving the polymer.

3. The release agent of claim 1 wherein the silicone base rubber is a heat-curable silicone base rubber.
4. The release agent of claim 3 wherein the heat-curable
5 silicone base rubber is an addition cure type silicone rubber.
5. The release agent of claim 3 wherein the heat-curable silicone base rubber is an organic peroxide cure type silicone rubber.
- 10 6. The release agent of claim 3 wherein the heat-curable silicone base rubber is a silicone-polyolefin copolymer rubber.
- 15 7. The release agent of claim 3 wherein the heat-curable silicone base rubber contains at least 0.1% by weight of an adhesion promoter.
8. A method of producing a silicone base rubber article,
20 comprising the step of molding a silicone base rubber in a mold treated with the release agent of claim 1.
9. The method of claim 8 wherein the silicone base rubber is a heat-curable silicone base rubber.
- 25 10. The method of claim 9 wherein the heat-curable silicone base rubber is an addition cure type silicone rubber.
11. The method of claim 9 wherein the heat-curable
30 silicone base rubber is an organic peroxide cure type silicone rubber.
12. The method of claim 9 wherein the heat-curable
35 silicone base rubber is a silicone-polyolefin copolymer rubber.

13. The method of claim 9 wherein the heat-curable silicone base rubber contains at least 0.1% by weight of an adhesion promoter.